Mercasol 845 AL

Professional anti corrosion treatment for car underbody

General

Mercasol 845AL, which is approved according to SS 18 65 12, is a solvent borne (aliphatic naphtha), wear resistant underbody corrosion protection agent, based on bitumen, wax and resin and have very good corrosion protection properties over a long period of time. The film properties of Mercasol 845AL prevents it from being chipped off by e.g. gravels. The product has been compatibility tested with the most of the vehicle brands different corrosion protection systems and is approved to be used on a major part of the different brands.

Range of application

Mercasol 845AL is meant for professional corrosion protection treatment of the underbody of vehicles where a lighter bronze coloured surface is desired. When priming on open surfaces before application of Mercasol 845AL the primary material recommendation is Mercasol 831ML.

Instructions for use

Surfaces to be treated shall be dry and free of rust, dirt, salt and oil or similar. We recommend usage of Mercasol 831 ML for cavities, flanges and joints on vehicles before treatment with Mercasol 845. Application is recommended to take place indoors at temperatures between 15 – 25° C.
Mercasol 845 AL is intended to apply with a airless high-pressure pump 1:26 > with a feeding pressure of 3 to 5 bar.
The drying time is depending on temperature and humidity, at +23°C and 50 % RH the drying time will be approx. 8 h. Prevent the vehicle of exposing for stone chip first week after treatment.

Package

42100408 / 20-lit can
42100701 / 60-lit barrel
42100721 / 208-lit barrel
42100761 / 208-lit lid barrel
42100800 / 1000-lit

Technical data

Color:	Bronze
Consistency:	Thick liquid
Type of film:	Elastic
Density at 20°C:	930 ± 20 kg/ m³
Dry content:	65 ± 3 %
Solvents:	White spirit
Film thickness:	450 µm wet / 250 µm dry layer
Application temperature:	15 - 35°C
Removal with:	Degreasing compound or white spirit
Storing time:	12 months
Storing temperature:	5 - 35°C

For further information we recommend the safety data sheet or instruction on package

Issue: 2015-01-14

Auson AB. Kungsbacka, Sweden
T: +46 (0)300-56 20 00
www.auson.se

Dessa anvisningar och information är avsedda att vägleda förbrukaren vid användning av produkten och lämnas utan förbindelse. Vid oklarhet tillråds egna prov eller skriftliga råd från oss.